



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C22F 1/04, C22C 21/00, 45/08	A1	(11) International Publication Number: WO 93/08314
		(43) International Publication Date: 29 April 1993 (29.04.93)

(21) International Application Number: PCT/US92/08618

(22) International Filing Date: 9 October 1992 (09.10.92)

(30) Priority data:
782,951 25 October 1991 (25.10.91) US

(71) Applicant: ALLIED-SIGNAL INC. [US/US]; 101 Columbia Road, P.O. Box 2245, Morristown, NJ 07962-2245 (US).

(72) Inventors: LASALLE, Jerry, C. ; 6 Valley Place, Upper Montclair, NJ 07043 (US). RAMANAN, V., R., V. ; 111 Richard Street, Dover, NJ 07801 (US). SKINNER, David, J. ; 14 Windswept Way, Long Valley, NJ 07853 (US).

(74) Agent: ROONEY, Gerard, P.; Allied-Signal Inc., Law Department (C.A. McNally), 101 Columbia Road, P.O. Box 2245, Morristown, NJ 07962-2245 (US).


(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, SE).

Published
With international search report.

(54) Title: STRENGTH ENHANCEMENT OF RAPIDLY SOLIDIFIED ALUMINUM-LITHIUM THROUGH DOUBLE AGING

(57) Abstract

A component consolidated from a rapidly solidified aluminum-lithium alloy containing copper, magnesium and zirconium is subjected to a preliminary aging treatment at a temperature of about 400 °C to 500 °C for a time period of about 0.5 to 10 hours; quenched in a fluid bath; and subjected to a final aging treatment at a temperature of about 100 °C to 250 °C for a time period ranging up to about 40 hours. The component exhibits increased strength and elongation, and is especially suited for use in lightweight structural parts for land vehicles and aerospace applications.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SK	Slovak Republic
CI	Côte d'Ivoire	LK	Sri Lanka	SN	Senegal
CM	Cameroon	LU	Luxembourg	SU	Soviet Union
CS	Czechoslovakia	MC	Monaco	TD	Chad
CZ	Czech Republic	MG	Madagascar	TC	Togo
DE	Germany	ML	Mali	UA	Ukraine
DK	Denmark	MN	Mongolia	US	United States of America
ES	Spain			VN	Viet Nam
FI	Finland				

**STRENGTH ENHANCEMENT OF RAPIDLY SOLIDIFIED
ALUMINUM-LITHIUM THROUGH DOUBLE AGING**

CROSS REFERENCE TO RELATED APPLICATIONS

5 This is a continuation-in-part of copending application Serial No. 672,990, filed March 21, 1991 which, in turn, is a continuation-in-part of Serial No. 517,774, filed May 2, 1990.

1. Field of Invention

10 The invention relates to rapidly solidified aluminum-lithium-copper-magnesium-zirconium powder metallurgy components having a combination of high ductility and high tensile strength; and more particularly to a process wherein the components are
15 subjected to thermal treatment which improves yield and ultimate strengths thereof with minimal loss in tensile ductility.

2. Brief Description of the Prior Art

20 The need for structural aerospace alloys of improved specific strength and specific modulus has long been present. It is known that the elements lithium, beryllium, boron, and magnesium can be added to an aluminum alloy to decrease its density. Conventional methods for producing aluminum alloys,
25 such as direct chill (DC), continuous and semi-continuous casting, yield aluminum alloys having up to 5 wt% magnesium or beryllium; but such alloys are inadequate for use in applications requiring a combination of high strength and low density. Lithium
30 contents of about 2.5 wt% have been satisfactorily incorporated into the lithium-copper-magnesium family of aluminum alloys, including those alloys designated 8090, 8091, 2090 and 2091. These alloys have copper and magnesium additions in the 1 to 3 wt% and 0.25 to
35 1.5 wt% range, respectively. In addition, zirconium is also added for grain refinement at levels up to 0.16 wt%.

- 2 -

The above alloys derive strength and toughness through the formation of several precipitate phases, which are described in detail in the Conference Proceedings of Aluminum-Lithium V, edited by T.H. Sanders and E.A. Starke, pub. MCE, (1989). An important strengthening precipitate in aluminum-lithium alloys is the metastable δ' phase which has a well defined solvus line. Thus, aluminum-lithium alloys are heat treatable, their strength increasing as δ' homogeneously nucleates from the supersaturated aluminum matrix.

The δ' phase consists of the ordered $L1_2$ crystal structure and the composition Al_3Li . The phase has a very small lattice misfit with the surrounding aluminum matrix and thus a coherent interface with the matrix. Dislocations easily shear the precipitates during deformation, resulting in the buildup of planar slip bands. This, in turn, reduces the toughness of aluminum lithium alloys. In binary aluminum-lithium alloys where this is the only strengthening phase employed, the slip planarity results in reduced toughness.

The addition of copper and magnesium to aluminum-lithium alloys has two beneficial effects. First, the elements reduce the solubility of lithium in aluminum, increasing the amount of strengthening precipitates available. More importantly, however, the copper and magnesium allow the formation of additional precipitate phases, most importantly the orthorhombic S' phase (Al_2MgLi) and the hexagonal T_1 phase (Al_2CuLi). Unlike δ' , these phases are resistant to shearing by dislocations and are effective in minimizing slip planarity. The resulting homogeneity of the deformation results in improved toughness, increasing the applicability of these alloys over binary

- 3 -

aluminum-lithium. Unfortunately, these phases form sluggishly, precipitating primarily on heterogeneous nucleation sites such as dislocations. In order to generate these nucleations sites, the alloys must be cold worked prior to aging.

Zirconium, at levels under approximately 0.15 wt%, is typically added to the alloys to form the metastable Al_3Zr phase for grain size control and to retard recrystallization. Metastable Al_3Zr consists of an Ll_2 crystal structure which is essentially isostructural with δ' (Al_3Li). Additions of zirconium to aluminum beyond 0.15 wt% using conventional casting practice result in the formation of relatively large dispersoids of equilibrium Al_3Zr having the tetragonal DO_{23} structure which are detrimental to toughness.

Much work has been done to develop the aforementioned alloys, which are currently near commercialization. However, the processing constraint imposed by the need for cold deformation has limited the application of these alloys to thin, low dimensional shapes such as sheet and plate. Complex, shaped components such as forgings are not amenable to such processing. Hence, conventional aluminum-lithium alloy forgings lack the combination of strength, ductility, and low density required for aerospace structural applications.

Summary of the Invention

The invention provides a method for increasing the tensile strength of a component composed of a rapidly solidified aluminum-lithium-copper-magnesium-zirconium alloy by subjecting the component to a multi-step aging treatment. Generally stated, the component is a consolidated article, formed from an alloy that is rapidly solidified and consists essentially of the formula $\text{Al}_{a-1}\text{Li}_a\text{Cu}_b\text{Mg}_c\text{Zr}_d$ wherein "a" ranges from about

- 4 -

2.1 to 3.4 wt%, "b" ranges from 0.5 to 2.0 wt%, "c" ranges from 0.2 to 2.0 wt%, and "d" ranges from about 0.2 to 0.6 wt%, the balance being aluminum. The aging treatment to which the component is subjected comprises the steps of subjecting the component to a preliminary aging treatment at a temperature of about 400°C-500°C for a time period ranging from about 0.5 to 10 hours; quenching the component in a fluid bath; and subjecting the component to a final aging treatment at a temperature of about 100°C-250°C for a time period ranging up to about 40 hours.

In addition, the invention provides a component consolidated from a rapidly solidified aluminum-lithium alloy of the type delineated, which component has been subjected to the multi-step aging treatment specified hereinabove.

It has been found that when specific components consolidated from rapidly solidified alloys of the composition delineated are subjected to the multi-step aging treatment specified, they exhibit increased strength and elongation, as compared with components that are thermally processed in a conventional manner. The improved combination of properties afforded by components of the invention renders them especially suited for lightweight structural parts used in automobile, aircraft or spacecraft applications.

Brief Description of the Drawings

The invention will be more fully understood and further advantages will become apparent when reference is made to the following detailed description of the preferred embodiment of the invention and the accompanying drawings in which:

FIG. 1 is a graph depicting the heat evolution/absorption vs. temperature as measured by differential scanning calorimetry for an

- 5 -

Al-2.6Li-1.0Cu-0.5Mg-0.6Zr alloy aged at 540°C for 2 hours and ice water quenched;

FIG. 2 is a graph for the alloys of Table I of the yield strength vs. aging temperature of a transverse specimen cut from an extruded bar aged for 2 hrs. followed by an ice water quench and subsequent aging for 16 hrs. at 135°C, the open rectangle providing data for a transverse specimen cut from an Al-2.5Li-1.07Zr extruded bar; the specimen being aged at 540°C for 2 hrs. was water quenched and subsequently aged at 135°C for 16 hours;

FIG. 3 is a graph of the ultimate tensile strength vs. aging temperature for specimens aged in the manner of the specimens of Fig. 2;

FIG. 4 is a graph of the tensile elongation vs. aging temperature for specimens aged in the manner of the specimens of Fig. 2; and

FIG. 5 is a graph depicting the ultimate strength vs. elongation for the alloys of Fig. 2 illustrating the improvement in properties extant along the diagonal away from the origin.

Description of the Preferred Embodiment

The invention provides a thermal treatment that increases the tensile strength of a low density rapidly solidified aluminum-base alloy, consisting essentially of the formula $Al_{b+a}Li_cCu_bMg_cZr_d$ wherein "a" ranges from 2.1 to 3.4 wt%, "b" ranges from about 0.5 to 2.0 wt%, "c" ranges from 0.2 to 2.0 wt%, "d" ranges from about 0.2 to 0.6 wt% and the balance is aluminum.

The thermal treatment to which the alloy is subjected involves several thermal process steps, i.e. 1) solutionization, 2) preliminary aging and 3) double aging as defined hereinafter. Solutionization refers to the absorption of lithium containing phases such as $Al_3Li(\delta')$, $AlLi(\delta)$, and/or lithium, copper, magnesium

- 6 -

containing phases, for example T_1 and S' phases (Al_2CuMg , Al_2CuLi , Al_2MgLi , etc.). Solutionization of these phases into the aluminum lattice occurs at temperatures above approximately $450^\circ C$. The alloy is
5 said to be solutionized when held above this temperature for sufficient time to dissolve these phases. A quench in a fluid bath is generally employed to prevent reformation of these phases upon cooling to room temperature.

10 Although the lithium, magnesium, and/or copper containing phases are dissolved at these temperatures and the alloy is solutionized with respect to these phases, the alloy is not solutionized with respect to the metastable phase having the $L1_2$ crystal structure
15 which consists essentially of the composition Al_3Zr , although certain amounts of Li, Cu, and/or Mg may be present in this phase.

The $L1_2$ phase, which is formed above $450^\circ C$, is comprised of the precipitates which result during the
20 thermal process step defined as the preliminary age. Surprisingly, this precipitate formation occurs simultaneously with the solutionization of the δ and δ' phases. Thus, above $450^\circ C$ both solutionization and preliminary aging is occurring.

25 Double aging includes two thermal process steps, the first step being the preliminary age above $450^\circ C$ for the formation of metastable $L1_2$ phase containing predominately Al and Zr, and the second step being a low temperature aging treatment between approximately
30 $120^\circ C$ and $200^\circ C$ where the Al_3Li phase precipitates.

Rapid solidification is defined as any cooling rate greater than about $10^3^\circ C/sec$ and includes powder processes such as melt atomization, spray forming and the like. Preferably, the alloys of the invention are
35 rapidly solidified by quenching and solidifying a melt

- 7 -

of a desired composition at a rate of at least about 10^5 °C/sec onto a moving, chilled casting surface. The casting surface may be, for example, the peripheral surface of a chill roll or the chill surface of an endless casting belt. Preferably, the casting surface moves at a speed of at least about 9,000 feet/minute (2750 m/min) to provide a cast alloy strip approximately 30-40 micrometers in thickness, which has been uniformly quenched at the desired quench rate. Such strip can be 4" or more in width, depending upon the casting method and apparatus employed. Suitable casting techniques include, for example, jet casting and planar flow casting through a slot-type orifice.

In accordance with the invention, the rapidly solidified and then compacted alloy or component is subjected to a preliminary thermal treatment at temperatures ranging from about 400°C to 500°C for a period of approximately 0.5 to 10 hours. While not being bound by theory, it is believed that this treatment dissolves elements such as Cu, Mg, and Li which may be microsegregated in precipitated phases such as δ' , δ , T_1 and S' . In addition, the thermal treatment produces an optimized distribution of cubic $L1_2$ particles ranging from about 5 to 50 nanometers in size. The alloy article is then quenched in a fluid bath, preferably held between 0° and 60°C. As used hereinafter in the specification and claims, the term "preliminary aging" is intended to define the thermal treatment described in the first sentence of this paragraph. The compacted article is then aged at a temperature ranging from about 100°C to 250°C. for a time period ranging up to about 40 hours to provide selected strength/toughness tempers. No cold deformation step is required during this thermal processing, with the result that complex shaped

- 8 -

components such as forgings produced from the aged component have excellent mechanical properties.

Preliminary aging below approximately 400°C results in a deleterious drop in tensile properties due to the formation of undesirable phases such as the δ (AlLi) phase. Preliminary aging above approximately 500°C results in an acceptable combination of tensile properties but does not result in the attainment of the optimum tensile strength since the volume fraction of precipitates is reduced. Grain coarsening may also occur at temperature beyond 550°C, further reducing strength.

Consolidated articles aged in accordance with the invention exhibit tensile yield strength ranging from about 400 MPa (58 ksi) to 545 MPa (79 ksi), ultimate tensile strength ranging from about 510 MPa (74ksi) to MPa (83 ksi), elongation to fracture ranging from about 4 to 9 %, and transverse notched impact energies ranging from about 1.5×10^{-2} to 2.8×10^{-2} Joules/mm², when measured at room temperature (20°C).

The following examples are presented to provide a more complete understanding of the invention. The specific techniques, conditions, materials, proportions and reported data set forth to illustrate the principles and practice of the invention are exemplary and should not be construed as limiting the scope of the invention.

EXAMPLES 1-3

Thermal processing in accordance with the invention was carried out on extruded bar made from rapidly solidified alloys having compositions (in wt%) listed in Table I. The ternary composition Al-2.5Li-1.0Zr was also produced via rapid solidification and is included for comparative purposes.

- 9 -

TABLE I

-
- | | |
|---|-------------------------------|
| | 1. Al-2.1Li-1.0Cu-0.5Mg-0.2Zr |
| | 2. Al-2.6Li-1.0Cu-0.5Mg-0.4Zr |
| 5 | 3. Al-2.6Li-1.0Cu-0.5Mg-0.6Zr |
-

EXAMPLE 4

Al-2.6Li-1.0Cu-0.5Mg-0.6Zr, made via rapid solidification and formed into an extrusion, was given a preliminary age at 540°C for 2 hours and ice water quenched. The heat evolution/absorption as a function of temperature was then measured using the technique of differential scanning calorimetry (DSC), shown in Figure 1. The peaks in Figure 1 represent the dissolution of precipitate phases during heating while the troughs represent precipitation. A precipitation reaction is represented by the trough centered at 450°C. It is this precipitation reaction which is responsible for the enhanced strength resulting from the preliminary aging treatment.

EXAMPLE 5

The tensile properties of consolidated articles formed by extrusion of the alloys listed in Table I and thermally processed in accordance with the method of the invention are listed in Table II. The extruded bars were given a preliminary age for 2 hours at temperatures between 400°C and 600°C and quenched into an ice water bath; subsequently, they were aged at 135°C for 16 hours. Transverse specimens were then cut and machined into round tensile specimens having a gauge diameter of 3/8 inches and a gauge length of 3/4 inches. Tensile testing was performed at room temperature at a strain rate of $5.5 \times 10^{-4} \text{ sec}^{-1}$.

- 10 -

TABLE II

	Composition (wt%)	0.2% YS (MPa)	UTS (MPa)	Elong. to fract. (%)	Impact Toughness Joule/mm ²
5	Aging Temp.				
	Al-2.6Li-1.0Cu-0.5Mg-0.2Zr				
	400°C	400	435	4.9	
10	440°C	410	495	7.2	
	490°C	395	500	6.3	
	540°C	350	470	8.0	2.6x10 ⁻²
	590°C	340	460	6.9	
	Al-2.6Li-1.0Cu-0.5Mg-0.4Zr				
15	540°C	410	535	9.4	1.9x10 ⁻²
	Al-2.6Li-1.0Cu-0.5Mg-0.6Zr				
	400°C	500	510	5.2	8.5x10 ⁻³
	440°C	490	535	6.9	1.6x10 ⁻²
20	490°C	470	540	7.7	2.1x10 ⁻²
	540°C	440	520	5.8	2.3x10 ⁻²
	590°C	395	515	8.3	2.6x10 ⁻²
	Al-2.5Li-1.07Zr				
25	540°C	410	425	9.5	2.2x10 ⁻²

Figures 2, 3, and 4 are graphs of the data listed in Table II. The graphs illustrate that the peak ultimate tensile strength (UTS) is a function of both zirconium content and temperature of the first aging treatment. For example, a peak UTS of 540 MPa is obtained for a 490°C preliminary aged Al-2.6Li-1.0Mg-0.6Zr.

Also included for comparative purposes in the Figures 2, 3, and 4 is the transverse tensile data for an Al-2.5Li-1.07Zr extrude bar. It is clear that the combination of tensile strength and elongation of the Al-Li-Cu-Mg-Zr alloys of this invention are superior to those of the Al-2.5Li-1.07Zr.

Fig. 5 is a graph of the ultimate tensile strength vs. notched impact energy for the alloys listed in Table II. The graph illustrates that the Al-Li-Cu-Mg-Zr alloys have a strength-toughness combination superior to the ternary Al-Li-Zr alloy.

- 11 -

EXAMPLE 6

This example illustrates that the enhanced strength resulting from control of the preliminary age is greater than and thus distinct from merely extending the aging time of the second low temperature aging treatment. The tensile yield strengths for an Al-2.6Li01.0Cu-0.5Mg-0.6Zr extrusion measured in the manner set forth in Example 5 are listed in Table III. Reducing the preliminary aging temperature from 540°C to 400°C results in a 14% increase in tensile strength compared with only 4% increase in strength when a 540°C preliminary aged specimen is aged for double the time 135°C.

Table III

Thermal Treatment	YS(MPa)
400°C-2hr ice WQ;135°C-16hr	500
540°C-2hr ice WQ;135°C-16hr	440
540°C-2hr ice WQ;135°C-32hr	460

EXAMPLE 7

This example illustrates that a precipitation reaction is occurring during the preliminary age above 450°C. Consolidated articles made from melt spun ribbon of the composition Al-2.6Li-1.0Cu-0.5Mg-0.6Zr were held at the temperatures listed in Table IV for 2 hrs. and water quenched.

Table IV

Temp°C	Rockwell B Hardness
400	44
450	47
500	49
550	48
600	41

- 12 -

The resulting hardness of the material was measured using the standard Rockwell hardness B scale. Table IV shows that the hardness is a function of temperature, the highest hardness occurring at 500°C. This increase
5 in hardness is ascribed to a classic precipitation phenomenon, in this case to the formation of the metastable L1₂ precipitate containing Zr.

Having thus described the invention in rather full detail, it will be understood that these details need
10 not be strictly adhered to but that various changes and modifications may suggest themselves to one skilled in the art, all falling within the scope of the invention as defined by the subjoined claims.

- 13 -

What is claimed is:

1. A process for increasing the strength of a rapidly solidified aluminum-lithium alloy component, comprising the steps of:

- 5 a. subjecting the component to a preliminary aging treatment at a temperature of about 400°C to 500°C for a time period from about 0.5 to 10 hours;
- b. quenching the component in a fluid bath; and,
- c. subjecting the component to final treatment at
- 10 a temperature of about 100°C to 250°C for a time period ranging up to about 40 hours, said component being a consolidated article formed from an aluminum-lithium alloy that is rapidly solidified and consists essentially of the formula $Al_{b-a}Li_aCu_bMg_cZr_d$ wherein "a" ranges from about 2.1 to 3.4 wt%, "b" ranges from about
- 15 0.5 to 2.0 wt%, "c" ranges from about 0.2 to 2.0 wt% and "d" ranges from about 0.2 to 0.6 wt%, the balance being aluminum.

2. A process as recited by claim 1, wherein said

20 component has the composition 2.6 wt% lithium, 1.0 wt% copper, 0.5 wt% magnesium and 0.6 wt% zirconium, the balance being aluminum.

3. A process as recited by claim 2, wherein said component, after final aging, has a 0.2% tensile yield

25 strength of 440 MPa, ultimate tensile strength of 530 MPa, and elongation to fracture of 6% and a transverse notched impact toughness of 2.3×10^{-2} Joules/mm².

4. A process as recited by claim 1, wherein said component has the composition 2.6 wt% lithium, 1.0 wt%

30 copper, 0.5 wt% magnesium and 0.4 wt% zirconium, the balance being aluminum.

5. A process as recited by claim 4, wherein said component, after final aging, has 0.2% tensile yield strength of about 410 MPa, ultimate tensile strength of

35 535 MPa, elongation to fracture of 9.4% and a

- 14 -

transverse notched impact toughness of 2.6×10^{-2} Joules/mm².

6. A component consolidated from an alloy that is rapidly solidified and consists essentially of the formula $Al_{b-a}Cu_bMg_cZr_d$ wherein "a" ranges from about 2.1 to 3.4 wt%, "b" ranges from about 0.5 to 2.0 wt%, "c" ranges from about 0.2 to 2.0 wt%, and "d" ranges from about 0.2 to 0.6 wt%, the balance being aluminum, said component having been subjected to a preliminary aging treatment at a temperature of about 400°C to 500°C for a time period of about 0.5 to 10 hours, quenched in a fluid bath and subjected to a final aging treatment at a temperature of about 100°C to 250°C for a time period ranging up to about 40 hours.

7. A component as recited by claim 6, wherein said alloy has the composition 2.6 wt% lithium, 1.0 wt% copper, 0.5 wt% magnesium and 0.6 wt% zirconium, the balance being aluminum.

8. A component as recited by claim 7, having a 0.2% tensile yield strength of 440 MPa, ultimate tensile strength of 530 MPa, elongation to fracture of 6% and a transverse notched impact toughness of 2.3×10^{-2} Joules/mm².

9. A component as recited by claim 6, wherein said alloy has the composition 2.6 wt% lithium, 1.0 wt% copper, 0.5 wt% magnesium and 0.4 wt% zirconium, the balance being aluminum.

10. A component as recited by claim 9, having 0.2% tensile yield strength of 410 MPa, ultimate tensile strength of 535 MPa and elongation to fracture of 9.4% and a transverse notched impact toughness of 2.6×10^{-2} Joules/mm².

1 / 5

Fig. 1





Fig. 2


Fig. 3



Fig. 4

Fig. 5



A. CLASSIFICATION OF SUBJECT MATTER

IPC5: C22F 1/04, C22C 21/00, C22C 45/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: C22F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO, A1, 9117281 (ALLIED-SIGNAL INC.), 14 November 1991 (14.11.91) page 11 - page 12; --	1-10
Y	EP, A1, 0158769 (ALLIED CORPORATION), 23 October 1985 (23.10.85) page 1, line 1 - page 3, line 17; page 4, line 10 - page 5, line 35; page 8, line 33 - page 9, line 19; --	1-10

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

28 January 1993

Date of mailing of the international search report

09.02.93

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patendaan 2
NL-2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Nils Engnell
Telephone No.

2

INTERNATIONAL SEARCH REPORT

Int. application No.

PCT/US 92/08618

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP, A1, 0412204 (ALUMINUM COMPANY OF AMERICA), 13 February 1991 (13.02.91), page 3, line 6 - line 23; page 4, line 36 - page 5, line 16; page 5, line 43 - page 6, line 16; figure 2	1-10
Y	WO, A1, 8700206 (ALLIED CORPORATION), 15 January 1987 (15.01.87) page 5, line 18 - page 7, line 18;	1-10
Y	WO, A1, 9112348 (ALLIED-SIGNAL INC.), 22 August 1991 (22.08.91) page 4, line 1 - line 23; page 7, line 10 - line 23;	1-10
A	EP, A1, 0273837 (CEGEDUR SOCIETE DE TRANSFORMATION DE L'ALUMINIUM PECHINEY), 6 July 1988 (06.07.88) page 3, line 7 - line 12;	1-10
A	WO, A1, 9115609 (ALLIED-SIGNAL INC.), 17 October 1991 (17.10.91)	1-10
A	Lu Lianda et al, "EFFECT OF HEAT TREATMENT ON THE MICROSTRUCTURES AND MECHANICAL PROPERTIES OF 2091 ALLOY, Aluminium-Lithium Alloys, Proceedings of the Fifth International Aluminium-Lithium Confe- rence Williamsburg, Virginia March 27-31, 1989. Vol II, p 889-897, MCE Publications, Birmingham (UK), document cited in the application	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

08/01/93

International application No.

PCT/US 92/08618

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A1- 9117281	14/11/91	AU-A- 7582291	27/11/91
EP-A1- 0158769	23/10/85	CA-A- 1228491	27/10/87
		DE-A- 3562493	09/06/88
		JP-A- 1272742	31/10/89
		JP-C- 1613624	15/08/91
		JP-B- 2036661	20/08/90
		JP-A- 60208445	21/10/85
		US-A- 4661172	28/04/87
EP-A1- 0412204	13/02/91	US-A- 4861391	29/08/89
WO-A1- 8700206	15/01/87	AU-B- 578828	03/11/88
		AU-A- 5774986	30/01/87
		CA-A- 1280342	19/02/91
		EP-A,B- 0229075	22/07/87
		JP-T- 62502295	03/09/87
WO-A1- 9112348	22/08/91	EP-A- 0514498	25/11/92
		US-A- 5091019	25/02/92
		US-A- 5106430	21/04/92
EP-A1- 0273837	06/07/88	FR-A- 2607521	03/06/88
		JP-A- 63143245	15/06/88
WO-A1- 9115609	17/10/91	US-A- 5045125	03/09/91